

SUPPORTÉ CAMOUFLAGE EXPANDED

SPÉCIFICATIONS / SPECIFICATIONS

CAMOUFLAGE

Épaisseur / Thickness	0.70mm +/-5%
Poids total / Total Weight	482gsm +/-5%
Largeur / Finish Width	54" +/-2%
Code de production / Production Code SC-259	VT3851 NS5CD1198-1
Élongation / Elongation (%)	MD 47.00 * CD 227.00
Résistance à la traction / Tensile Strength (KG/3cm)	JASO M313-83 Weft 17.10 * Warp 11.88
Résistance à la déchirure / Tear Strength (KG/4cm)	JASO M313-83 Weft 3.50 * Warp 2.68
Résistance à l'éclatement / Burst Strength (KG/2cm)	JASO M313-83 9.00
Adhérence de la surface / Adhesion of Surface (KG/3cm)	Weft 2.10 * Warp 1.15
Résistance aux feu / Flammability Requirements	FMVSS302
Résistance au froid / Cold Crack Requirements	-10°C
Anti-UV	100 heures / hours classe / class 5.0 per ASTM D4329-13
Surface brillante / Shiny Surface	REICH: MIT-1609004-GM 2.20—3.10gu
Dureté / Hardness	70 phr
Embossage/ Emboss	HA10
Endos / Backing	Rayonne polyester / Polyester Rayon
Résistance à l'abrasion / Abrasion Resistance	ASTM D4157 110,000 cycles
MIGRATION DE CERTAINS ÉLÉMENTS MIGRATION OF CERTAIN ELEMENTS	CLASSE ENVIRONNEMENTAL EN71 PART3 ENVIRONMENTAL GRADE EN71 PART3

UTILISATION:

Banquette, banc de bar, banc de cuisine, sofa et beaucoup plus.

Nettoyer avec un tissu souple, du savon doux et de l'eau froide.

Formulés et fabriqués pour répondre aux exigences des tests en laboratoire, toutes les données de performances typiques dans les tests spécifiés ne doivent pas être interprétées comme comportements en conditions réelles.

APPLICATIONS / USAGE:

Clean with soft cloth, mild soap and cold water.

Formulated and manufactured to meet requirements of testing under laboratory conditions and any data to typical performance in specified tests should not be construed to imply behavior under actual conditions.



110 rue Richer
Lachine, Qc.
H8R 1R2

Tel: 514-369-8980 1-877-369-8980

Fax: 514-369-8918 1-888-577-3872

www.duraplas.com sales@duraplas.com

#SPC016-1018