

YUKON

SPÉCIFICATIONS / SPECIFICATIONS

YUKON

Épaisseur / Thickness		.80mm +/-5%
Poids total / Total Weight		483gsm +/-5%
Largeur / Finish Width		54" +/-2%
Code de production / Production Code SC-292		VT5065 NS7BD1098-8
Volatilité / Volatility	(%)	.04 -100°C x 1heure/hour
Étirement / Stretching	(%)	ND 1% max TD 1% max
Résistance à la traction / Tensile Strength	(KG/3cm)	Warp 11.55 * Weft 17.65
Résistance à la déchirure / Tear Strength	(KG)	JIS K 6772 MD 4.5min * TM 3.3min
Résistance à l'éclatement / Burst Strength	(KG/2cm)	7.25
Adhérence de la surface / Adhesion of Surface	(KG/3cm)	Warp 1.36 * Weft 1.78
Résistance aux feu / Flammability Requirements		FMVSS302
Résistance au froid / Cold Crack Requirements		-40°C
Anti-UV		100 heures / hours classe / class 5.0 per ASTM D4329-13
Séparation / Separation	(KG/30mm)	JIS K 6772 MD 1.8 min TD 1.5 min
Rétrécissement / Shrinkage	(%)	JIS K 6772 MD 1% max TD 1% max
Tension / Tension	(kg/30mm)	JIS K 6772 MD 35.2 min TD 9.9 min
Endos / Backing		30 TE
Résistance à l'abrasion / Abrasion Resistance		ASTM D4157 110,00 cycles
MIGRATION DE CERTAINS ÉLÉMENTS		CLASSE ENVIRONNEMENTAL EN71 PART3
MIGRATION OF CERTAIN ELEMENTS		ENVIRONMENTAL GRADE EN71 PART3

UTILISATION:

Rembourrage commercial, sofa, chaises, intérieur auto.

Nettoyer avec un tissu souple, du savon doux et de l'eau froide.

Formulés et fabriqués pour répondre aux exigences des tests en laboratoire, toutes les données de performances typiques dans les tests spécifiés ne doivent pas être interprétées comme comportements en conditions réelles.

APPLICATIONS / USAGE:

Clean with soft cloth, mild soap and cold water.

Formulated and manufactured to meet requirements of testing under laboratory conditions and any data to typical performance in specified tests should not be construed to imply behavior under actual conditions.



110 rue Richer
Lachine, Qc.
H8R 1R2

Tel: 514-369-8980 1-877-369-8980
Fax: 514-369-8918 1-888-577-3872
www.duraplas.com sales@duraplas.com

#SPC021-1018